

CURTIS S 60 A2

Description

CURTIS S 60 A2 is a water-miscible coolant lubricant and contains mineral oil, lubricity improvers as well as anionic and non-ionic emulsifiers.

Technical data

concentrate	
colour:	brown
density (15 °C):	0,94 g/cm ³
mineral oil content :	> 65 %
Emulsion	
Appearance:	milky
pH-valuet (5%ig):	8,8 - 9
Corrosion test (Filter/cast-iron chips):	Corrosion free > 6% (DIN 51360/2)

refraction factor: 0,9

Operational areas / Applications

CURTIS S 60 A2 is usable for middle - heavy machining operations on steel (low alloy / high-alloyed steel) as well as aluminium materials and non-ferrous metals (mixed processing).
The product can also be used for grinding operations.

operation	Recommended concentration for use
machining (turning, milling, drilling, thread cutting, reaming, sawing) of steel alloys	from 5% to 10%
of aluminium alloys, non-ferrous m.	from 6% to 12%
grinding of steel, aluminium	from 5% to 7%

Mixing with water should be realized with a mixing unit.

Special features

- ✓ *good skin compatibility*
- ✓ *forms oily protective film*
- ✓ *free of boron and amines*
- ✓ *less foaming even in soft water*

Technical data are representative values. All recommendations are without any obligation. Users should verify current specifications with Curtis and ascertain that products as supplied are suitable for intended applications.

Revision date: 06/2013